## Corazza S.r.l.

Via Sandro Pertini, 37 40062 Molinella (BO) Italy Tel. +39-051/881877 Fax +39-051/6902146 e-mail: info@corazzagroup.com



Technical Data Sheet no. 5

Revision no. 3

Revision date 30.03.19

## **TECHNICAL DATA SHEET**

## Data obtained from our supplier's technical data sheet

Product identifier: M2M / M4M / M5M cell solid polymeric material

Composition	E.V.A. + P.E. Expanded
Cell structure	Closed
Colour	Multicolour
Density (UNI EN 10902)	0.170/0.180 Kg/dm <sup>3</sup>
Water absorption (ASTM D 1056)	4.30%
Material stability temperature range	-10° C + 70 ° C
Elongation at break – (ASTM D 412)	> 150%
Tensile strength (ASTM D 412)	2.6 MPa
Tear strength (ASTM D 624)	0.83 kN/m
Compression strength (ASTM 1056/85)	1.4 MPa
Hardness	85 Shore 00

The information provided above is merely to be considered as guidance; since ambient conditions of use are generally not the same as those of test methods, technical data must be considered purely guideline and do not imply responsibility on the part of Corazza srl.