



**TECHNICAL DATA SHEET**

**Data obtained from our supplier's technical data sheet**

Product identifier: **TX175 – cellulose fibres with added additives**  
Thickness: 1.75 mm

Technical features	Typical value	Minimum/maximum value
Thickness	1.78 mm	1.75/1.89
Width of sheet/roll	Order (cm)	130/166
Sheet length	Order (cm)	50/200
Roll length	Order (m)	
Standard sheet size	125x150 cm	
Number of sheets per pallet	450	
Density	0.570 g/cm <sup>3</sup>	
Taber stiffness	2010 g/cm	1610 2410
	1195 g/cm	960 1430
	4.0%	2.5 6
Moisture		
Taped Mullen	1500 kPa	
Resistance..Hot melt	600 N	
Water absorption after 2 hours	%	30%
Wet abrasion resistance	2 on scale 1-6	

This product complies with the amendment of the 2nd German Health Ministry Decree TRGS 614 concerning consumer goods, and therefore does not contain colourants which may release the amines listed in the decree in case of disassociation; it does not contain hexavalent chromium; the pentachlorophenol or other chlorinated phenol content is below 0.5 mg/kg; and it does not contain TBT.